

METALLURGY

E

S.No.	CONTENTS	Page
1.	Introduction	141
2.	Concentration of the ore	141
3.	Conversion of concentrated ore into oxide form	144
4.	Reduction of the metal oxide	146
5.	Refining of the metal	149
6.	Ellingham diagram	156
7.	Exercise-I (Conceptual Question)	161
8.	Exercise-II (Previous Years Questions)	165
9.	Exercise-III (Analytical Questions)	167
10.	Exercise-IV (Assertion & Reason)	168

NEET SYLLABUS

General Principles and Processes of Isolation of Elements : Principles and methods of extraction- concentration, oxidation, reduction electrolytic method and refining; occurrence and principles of extraction of aluminium, copper, zinc and iron.

OBJECTIVES

After studying this unit, you will be able to :

- *explain the terms minerals, ores, concentration, benefaction, calcination, roasting, refining, etc.;*
- *understand the principles of oxidation and reduction as applied to the extraction procedures;*
- *apply the thermodynamic concepts like that of Gibbs energy and entropy to the principles of extraction of Al, Cu, Zn and Fe;*
- *explain why reduction of certain oxides like Cu_2O is much easier than that of Fe_2O_3 ;*
- *explain why CO is a favourable reducing agent at certain temperatures while coke is better in some other cases;*
- *explain why specific reducing agents are used for the reduction purposes.*

An excellent man, like precious metal, is in every way invariable; A villain, like the beams of a balance, is always varying, upwards and downwards.

John Locke

METALLURGY

4.1 INTRODUCTION

Metallurgy : The branch of chemistry which deals with the method of extraction of metals from their ores by profitable means.

Metal : The element which tends to form positive ion is called a metal.

Minerals : The various compounds of metals which occur in the earth's crust and are obtained by mining are called minerals. In earth crust order of abundance of elements is. $O > Si > Al > Fe$

A mineral may be single compound or a mixture.

Ore : The mineral from which a metal can be extracted **profitably** and **easily** is called an ore.

All ores are minerals but all minerals are not ores. (T/F)

Type of Ores :

(I) **Combined Ore** : Metals placed above H in electrochemical series are generally reactive i.e. why they generally found in combined state.


(a) **Halide ore / Sulphate ore / Oxy ore** : Metals are highly reactive ($Li \rightarrow Mg$)

(b) **Oxide ore** : Reactive metal (Al to Sn)

(c) **Sulphide ore** : Metal placed near H or below H. (Pb, Hg, Cu, Ag)

(II) **Native Ore** : Metal placed below H in electrochemical series are generally found in native state.
(Ag, Au, Cu, Pt etc.)

Gangue or matrix : The undesirable impurities present in an ore are called **gangue**.



4.2 STEPS INVOLVED IN THE EXTRACTION OF METALS

The extraction of a metal from its ore is completed in the following four steps.


- | | |
|------------------------------|---|
| (A) Concentration of the ore | (B) Conversion of concentrated ore into oxide form. |
| (C) Reduction of the metal | (D) Refining of the metal. |

(A) Concentration of the ore or dressing or benefaction

The removal of impurities from the ore is called its concentration or to increase the concentration of ore in ore sample. Two process – (1)Physical (2) Chemical

(1) PHYSICAL :

(i) **Gravity separation (Levigation)** : This method of concentration of the ore is based on the difference in the specific gravities of the ore and the gangue particles. Powdered ore is agitated with a running stream of water. The lighter gangue particles are taken away by water while heavier ore particles settle down.
Ex. Oxygenated ore



Hydraulic classifier

(ii) Froth Floatation method

This method is mainly employed for the concentration of sulphide ores.

The method is based on the different wetting characteristics of the gangue and the sulphide ore with water and oil. The gangue preferentially wetted by water and the ore by oil.

The crushed ore along with water is taken in a floatation cell. Various substances are added depending on the nature of the ore and a current of air is blown in. The substances added are usually of three types.

(a) Frothers :- They generate a stable froth which rises to the top of the tank.

Example of frother is pine oil, Eucalyptus oil, fatty acids etc.

(b) Collectors or floating agents :- These attach themselves by polar group to the granules of the ores which then become water repellent and pass on into the froth.

Example: sodium ethyl xanthate, pine oil and fatty acid.



(c) Froth stabilisers : To stabilise froth.

Ex. Cresol, Aniline etc.

(d) Depressants :- These reagents activate or depress the floatation property and help in the separation of different sulphide ores present in a mixture.

e.g. NaCN.

Impurity of ZnS in PbS ore removed by NaCN




[Froth floatation process]

- Sometimes, it is possible to separate two sulphide ores by adjusting proportion of oil to water or by using 'depressants'.
- For example, in case of an ore containing ZnS and PbS, the depressant used is NaCN. It selectively prevents ZnS from coming to the froth but allows PbS to go along with the froth.

(iii) **Magnetic separation:-**

If either the ore or the gangue (one of these two) is capable of being attracted by a magnetic field, then such separations are carried out (e.g. in case of iron ores)

- e.g.
- SnO_2 having the impurities of $\text{FeWO}_4 + \text{MnWO}_4$ (Wolframite)
 - $\text{FeO} \cdot \text{Cr}_2\text{O}_3$ having the impurities of SiO_2 .





2. **CHEMICAL SEPARATION (LEACHING)** : In this process we use suitable agent which react with ore to form water soluble complex while impurities remain insoluble. Applicable for Al, Ag, Au.


- (a) **Aluminium** :
- Red Bauxite $\rightarrow \text{Al}_2\text{O}_3 \cdot 2\text{H}_2\text{O} + \text{Fe}_2\text{O}_3$ (Major impurity)
 - White Bauxite $\rightarrow \text{Al}_2\text{O}_3 \cdot 2\text{H}_2\text{O} + \text{SiO}_2$ (Major impurity)

(I) **RED BAUXITE** : Two processes

- (i) **Baeyer's process** : NaOH is used.





- (ii) **Hall's process** : Na_2CO_3 is used.





(II) **WHITE BAUXITE** : One process.

Serpeck's process : $(\text{C} + \text{N}_2)$ is used



(b) Ag and Au (CYANIDE PROCESS)








(B) Conversion of concentrated ore into oxide form

Calcination and roasting

(a) **Calcination** : Calcination is a process in which ore is heated, generally in the absence of air, to expel water from a hydrated or hydroxide ore and oxide or carbon dioxide from a carbonate ore at temperature below their melting points.


For Example: All carbonates, hydrated ore and hydroxide ore

**Advantages of Calcination :-**




- Moisture is removed.
- Organic matter is destroyed
- The hydroxide and carbonates ores are converted into their oxides.
- The ore become porous and easily workable

(b) **Roasting** : The removal of the excess sulphur contained in sulphide ores in the form of SO_2 by heating in an excess of air is called roasting.

The concentrated sulphide ore is heated in reverberatory furnace, below its melting point in the presence of an excess of air with or without the addition of an external substance.

**Thermal reduction**

Some less stable metal oxide further decompose into metal and oxygen.

**Partial roasting**


Roasting in Fe metallurgy



Haematite




Magnetite




Siderite

Roasting → to prevent wastage of Fe as slag in reduction step




In reduction step






Advantages of Roasting :-

(i) Excess of sulphur is removed as volatile oxide.



(ii) The metal sulphide is converted into metal oxide.

(iii) Impurities of arsenic, antimony & phosphorous are removed as their volatile oxides.



• For PbS, CuS and HgS partial roasting is carried out because these sulphide ore easily convert into metal by auto reduction process.

BEGINNER'S BOX-1

1. Match the following :-

Ore

Main element

(A) Malachite

(P) Fe

(B) Siderite

(Q) Pb

(C) Cerrusite

(R) Zn

(D) Pyrolussite

(S) Cu

(E) Wurtzite

(T) Mn

(1) A-S, B-Q, C-P, D-T, E-R

(2) A-S, B-P, C-Q, D-T, E-R

(3) A-Q, B-S, C-P, D-T, E-R

(4) A-R, B-Q, C-P, D-T, E-S

2. Assertion : Froth floatation is concentration method mainly used for sulphide ores.

Reason : Metal sulphides are highly soluble in water.

(1) A

(2) B

(3) C

(4) D

3. Assertion : In cyanide process, the leaching is accomplished using NaCN.

Reason : CN^- ion reduces Ag, Au & Zn ions in the process.

(1) A

(2) B

(3) C

(4) D

4. Match the ores listed in Column-I with their correct chemical formula listed in Column-II.

Column I

Column II

(A) Cassiterite

(p) FeCO_3

(B) Siderite

(q) SnO_2

(C) Cerussite

(r) PbSO_4

(D) Anglesite

(s) PbCO_3

(1) A-q, B-p, C-s, D-r

(2) A-r, B-p, C-s, D-q

(3) A-p, B-q, C-s, D-r

(4) A-q, B-p, C-r, D-s

5. Which of the following contains both Mg & Ca :
 (1) Magnesite (2) Calamine (3) Carnelite (4) Dolomite
6. Argentite is an ore of:-
 (1) Iron (2) Gold (3) Platinum (4) Silver
7. If Bauxite consists of SiO_2 as impurity, this process is employed :-
 (1) Hall's process (2) Bayer's process (3) Hoop's process (4) Serpeck's process
8. The impurities present in the ore is called:-
 (1) Slag (2) Flux (3) Alloy (4) Gangue
9. $\text{Ag}_2\text{S} + \text{NaCN} \longrightarrow \text{A}$, $\text{A} + \text{Zn} \longrightarrow \text{B}$
 B is a metal. Hence A and B :-
 (1) $\text{Na}_2[\text{Zn}(\text{CN})_4]$, Zn (2) $\text{Na}[\text{Ag}(\text{CN})_2]$, Ag (3) $\text{Na}[\text{Ag}(\text{CN})_4]$, Ag (4) $\text{Na}_3[\text{Ag}(\text{CN})_4]$, Ag
10. Chemical leaching is useful in the concentration of:-
 (1) bauxite (2) copper pyrites (3) cassiterite (4) None

(C) **Reduction to the metal :**


The calcined or roasted ore is then reduced to the metallic state by either of the following method :

(I) **Chemical reduction :**


(i) **Reduction by carbon (Smelting)**


"Reduction of the oxide with carbon at high temperature is known as smelting".

The oxides of less electropositive metals like Pb, Zn, Fe, Sn, Cu etc. are reduced by strongly heating them with coal or coke, in the blast furnace.




Example - Reaction in blast furnace :-






FLUX : Substance used to convert non fusible impurities into fusible one. Three types of flux are used.

(a) **Acidic Flux** : Substance used to remove basic impurities (metal oxide)




Acidic flux are non metal oxide (SiO₂, P₂O₅ etc.)

(b) **Basic flux** : Substance used to remove acidic impurities (non metal oxide)






Basic flux are metal oxide. (CaO, MgO, etc.)

(c) **Neutral flux** : Substance used in electrolytic reduction to decrease the fusion temperature and to increase the conductivity of the solution by providing free ions.



Smelting in Cu-metallurgy





imp flux

(ii) **Alumino thermite process or thermite welding process** : In this process those metal oxide will be reduced which required high temperature and at high temperature carbon react with metal to form metal carbide.

In this process we use aluminium as a reducing agent due to :-

(i) Al has greater affinity towards oxygen as it forms most stable oxide (Al₂O₃)

(ii) This reaction is highly exothermic in nature and once it start it will continue till all the metal oxide is reduced into metal.





Note : Reaction (b) is used in welding of railway tracks.

(II) Self reduction




Compounds of certain metals are reduced to metal without using any additional reducing agent. ores of Cu, Pb, Hg etc.

Their sulphide ores are partially roasted to give some oxide. This oxide is now reduced to the metal by the remaining sulphide ore at elevated temperatures in the absence of air. The process is known as self reduction.




Self reduction for Pb :-




Self reduction in Cu Metallurgy or bessemerisation




gangue flux




Bessemer convertor



(III) Metal displacement method : In this method, compound is reacted with a more electropositive & more reactive metal which displaces, the metal from the solution.



Kroll's Process





(IV) Electrolytic reduction

This process is mainly used for the extraction of highly electropositive metals. I A, II A & Al

Electrolysis is carried out in a large cell and a small amount of another suitable electrolyte is added which:

- Lowers the melting point of the main electrolyte
 - Enhances its conductivity
 - Reduces corrosion troubles
- e.g. Manufacture of metallic sodium (Down's process)

Molten NaCl containing a little CaCl_2 is electrolysed between graphite anode and iron cathode. The various reactions that take place are :




Hall heroult process :


This process is used for extraction of Al from alumina. The extraction of Al from Al_2O_3 is quite difficult because

- Fusion temperature of Alumina is quite high (2050°C). Even more than boiling point of Al (1150°C).
- It is a bad conductor of electricity. To overcome these difficulties we mix some amount of neutral flux [$\text{Na}_3\text{AlF}_6 + \text{CaF}_2$]. Neutral flux provides free ions to the solution which decreases the fusion temperature of Alumina from 2050°C to 950°C .


- (i) **From cryolite** $\rightarrow$ $\text{AlF}_3 \longrightarrow \text{Al}^{+3} + 3\text{F}^-$
At cathode : $\text{Al}^{+3} + 3\text{e}^- \rightarrow \text{Al}$ (reduction)




So at anode O_2 gas is liberated which on reaction with graphite anode convert into CO_2 & destroy the anode.



- (ii) **From Al_2O_3**



The main drawback of this process is that anode should be changed frequently.



REFINING OF METALS

Metals obtained by the reduction of its compound still contains some objectionable substance and have to be refined. Depending upon the nature of the metal and impurities, the following methods are used for purification of the metals.


(I) Physical Process :

- (i) **Liquation** : This method is used for the refining of metals having low melting point and are associated with high melting impurities.

Ex. Pb, Sn, Sb and Bi.

The impure metal is heated on the sloping hearth of a furnace.


The pure metal flows down leaving behind the non-fusible impurities on the hearth.



(ii) **Distillation** : Metals having low boiling point are refined by this method, for example, zinc, cadmium and mercury.



(iii) **Zone refining** : Metals of very high purity are obtained by zone refining. This refining method is based on the fact that impurities tend to remain dissolved in molten metal.

Ge, Si and Ga used as semiconductors are refined in this manner.





(II) CHEMICAL PROCESS :-

(i) **Cupellation** : This process is used to purify silver containing the impurities of Pb. This process is used when impurity have greater affinity towards O_2 while metal does not have.




(ii) **Poling** : Used to purify Cu, Pb.

This process is used for the metal having the impurity of their own oxide. In this process a green wooden pole is heated with molten metal, which provide C and H to metal oxide which reduce impurity of metal oxide to metal.



(iii) **Bessemerisation** : Actually it is the key principle involve to removal of impurities by oxidation with air being blown oxidise to molten metal.

Impure metal is heated in a furnace and a blast of compressed air is blown which oxidise the impurity into their oxides and that can be removed in the form of slag.



(III) ELECTRO-REFINING OF METALS

Metals such as Cu, Ag, Zn, Sn, Pb, Al, Ni, Cr are refined by this method.

The impure metal is made the anode of an electrolytic cell, while cathode is thin plate of pure metal.

Electrolyte is the solution of a salt of the metal.

On passing the electric current pure metal from the anode dissolves and gets deposited at the cathode.

The soluble impurities go into the solution while insoluble or less electropositive impurities settle down below the anode as **anode mud** or sludge. For Example

– *Electrorefining of Copper*

Anode	:	Blister copper (98%)
Cathode	:	Pure copper
Electrolyte	:	An aqueous solution of CuSO_4 (15%) + 5% dil H_2SO_4

– *Electrorefining of Silver*

Anode	:	Impure silver
Cathode	:	Pure silver
Electrolyte	:	Aq AgNO_3 + 1% dil HNO_3 on passing electricity impure anode dissolves and pure Ag is deposited at the cathode.

– *Electrorefining of Pb (Bett's process)*

Anode	:	Impure lead.,	Cathode	:	Pure lead.
Electrolyte	:	A mixture of PbSiF_6 and H_2SiF_6			

– *Electrorefining of Al (Hoope's process)*

Anode	:	Impure Al,	Cathode	:	Pure Al
Electrolyte	:	A mixture of Na_3AlF_6 + CaF_2			

(IV) Vapour Phase Refining (Thermal decomposition)

(i) Van - Arkel process :


This method is very useful for removing all the oxygen & nitrogen present in the form of impurity.

(i) Employed to get metal in very pure form of small quantities.


(ii) In this method, the metal is converted into a volatile unstable compound (e.g. iodide), and impurities are not affected during compound formation.

(iii) The compound thus obtained is decomposed to get the pure metal.

(iv) Employed for purification of metals like titanium and zirconium.



Impure



(ii) Mond's process

(i) Nickel is purified by using CO gas. This involves the formation of nickel tetracarbonyl.



BEGINNER'S BOX-2

- Copper matte consists of :-
 - (1) Copper oxide and ferrous sulphide
 - (2) Copper sulphide and ferrous oxide
 - (3) Copper sulphide and ferrous sulphide
 - (4) Copper oxide and ferrous oxide
- Product obtained after Bessemerisation is called as...because.....
 - (1) Concentrated copper ; copper percentage is high
 - (2) Copper matte ; of its appearance
 - (3) Blister copper ; of its appearance
 - (4) Ultra pure copper ; 100 percent copper
- Matte is obtained after this step -
 - (1) Froth floatation
 - (2) Roasting
 - (3) Smelting
 - (4) Refining
- Copper glance istype of ore -
 - (1) Carbonate
 - (2) Sulphide
 - (3) Oxide
 - (4) Sulphate
- High purity copper is obtained by -
 - (1) Zone refining
 - (2) Poling
 - (3) Electrolytic refining
 - (4) Cupellation
- The function of flux during the smelting of ore is:-
 - (1) To make the ore porous
 - (2) To remove gangue
 - (3) To facilitate reduction
 - (4) To facilitate oxidation
- The following equation represents a method of purification of nickel by :-


$$\text{Ni (impure)} + 4\text{CO} \xrightarrow{320\text{K}} \text{Ni(CO)}_4$$

$$\xrightarrow{420\text{K}} \text{Ni (pure)} + 4\text{CO}$$
 - (1) Cupellation
 - (2) Mond's process
 - (3) Van Arkel method
 - (4) Zone refining
- The slag obtained during the extraction of copper from copper pyrites is composed of :-
 - (1) Cu_2S
 - (2) CuSiO_3
 - (3) FeSiO_3
 - (4) SiO_2
- Which of the following reaction is a part of Hall's process :-
 - (1) $\text{Al}_2\text{O}_3 + 2\text{NaOH} \rightarrow 2\text{NaAlO}_2 + \text{H}_2\text{O}$
 - (2) $\text{Fe}_2\text{O}_3 + 2\text{Al} \rightarrow 2\text{Fe} + \text{Al}_2\text{O}_3$
 - (3) $\text{AlN} + 3\text{H}_2\text{O} \rightarrow \text{Al(OH)}_3 + \text{NH}_3$
 - (4) $\text{Al}_2\text{O}_3 \cdot 2\text{H}_2\text{O} + 2\text{Na}_2\text{CO}_3 \rightarrow 2\text{NaAlO}_2 + \text{CO}_2 + 2\text{H}_2\text{O}$
- Which method of purification is represented by the following equations

$$\text{Ti} + 2\text{I}_2 \xrightarrow{523\text{K}} \text{TiI}_4 \xrightarrow{1700\text{K}} \text{Ti} + 2\text{I}_2$$
 - (1) Cupellation
 - (2) Poling
 - (3) Van Arkel
 - (4) Zone refining


Al

Ore - Bauxite $\text{Al}_2\text{O}_3 \cdot 2\text{H}_2\text{O}$





Au


Ore - Auriferous Rock



Reaction involved :




Ag

Ore - Argentite Ag_2S **Reaction involved :**




- (a) $\text{Ag}_2\text{S} + 4\text{NaCN} \rightleftharpoons 2\text{Na}[\text{Ag}(\text{CN})_2] + \text{Na}_2\text{S} \xrightarrow{+\text{O}_2 + \text{H}_2\text{O}} \text{Na}_2\text{SO}_4 + \text{'S'} + 2\text{NaOH}$
 $\Rightarrow \text{O}_2$ is used to make reaction irreversible which remove Na_2S as $\text{Na}_2\text{SO}_4 + \text{S}$
- (b) $2\text{Na}[\text{Ag}(\text{CN})_2] + \text{Zn} \longrightarrow \text{Na}_2[\text{Zn}(\text{CN})_4] + \text{Ag} \downarrow$

Cu


Ore - CuFeS_2 copper pyrites

Reaction involved :

(a) **Roasting step**






Very less



(b) **Smelting step :-**





Cu_2S remain unaffected again becoz carbon reduction occurs only for oxide and not for sulphide.



Slag




(c) **Bessemer converter reaction :-**







Blister Cu

Fe



Reaction involved :

(1) **Roasting step :-**



FeO reacts with SiO_2 to give FeSiO_3 as slag.

Hence to prevent the formation of FeSiO_3 .

FeO is converted into Fe_2O_3 which does not react with SiO_2 due to high L.E.

GOLDEN KEY POINTS

● Types of Iron :-

Pig iron → Cast iron → Steel iron → Wrought iron

(i) Cast iron or pig iron

It is most impure form of Iron and contains the highest proportion of carbon (2.5 - 4 %) along with traces of S, P, Mn and Si. Cast iron contain 2.5 to 4.3 & pig contain 2.5 to 5%.

(ii) Wrought iron (Fibrous iron) or malleable iron

It is the purest form of iron and contains minimum amount of carbon (0.12 - 0.25%) and less than 5% of other impurities.

(iii) Steel

It is the most important form of iron and finds extensive applications. As far as carbon content (impurity) is concerned it is midway between cast iron and wrought iron, it contains 0.25- 2% carbon. Thus all the three forms of iron differ in their carbon contents, both iron and steel are obtained from cast iron.

Order of M.P. WI > Steel > CI or PI

- Useful gas NH_3 is evolved in the leaching of bauxite by serpeck's process.
- In the electrolytic reduction of Al_2O_3 , cryolite (Na_3AlF_6) is added along with CaF_2 (fluorspar) to-
 - decrease m.p. of Al_2O_3
 - decrease viscosity of electrolyte (CaF_2 is used)
 - increase conductivity
- In the electrolytic reduction, graphite anode gets corroded or finished due to reaction with O_2 liberated at anode, hence it had to be changed periodically.
- In the electrolytic refining (4th step) no electrodes are used. In the Hoope's process molten pure Al is used as cathode and molten impure Al is used an anode.


4.3 THERMODYNAMICS OF REDUCTION PROCESSES (ELLINGHAM DIAGRAM)


It is explanation of the feasibility of pyrometallurgical process by using gibbs equation $\Delta G = \Delta H - T\Delta S$

If $\Delta G = -ve$ Process is stable or Spontaneous

$\Delta G = +ve$ or Less -ve then process is Unstable or non-Spontaneous

When pyrometallurgical process contains more than one type of reaction then stability of reaction can be explain by Ellingham diagram. Ellingham diagram contains plot ΔG vs T .






$$\Delta G = +Ve$$



According to Ellingham diagram, the metal below can reduce the oxide of metal above it in the curve, as affinity of metal below for oxygen is more.

Example Al Metal can reduce Cr_2O_3 but can not reduce MgO & CaO .

At very high T after 'A' Point Al metal can reduce MgO because Formation of MgO contains less -ve ΔG .



According to diagram at high T (710°C OR above 710°C) Oxidation of C contains more -ve ΔG so at high T 'C' is good Reducing agent.


At Low T (below 710°C) Oxidation of CO contains more -ve ΔG so at Low T, CO is good Reducing agent.

BEGINNER'S BOX-3

- The appropriate flux for removing FeO will be
 (1) SiO_2 (2) CaO (3) MgO (4) Al
- Match the following :-

Metallurgical process	Methods
(A) Copper glance $\rightarrow \text{Cu}$	(P) Leaching by NaOH followed by electrolytic reduction
(B) Bauxite $\rightarrow \text{Al}$	(Q) Froth flotation, partial roasting & self reduction.
(C) Cerussite $\rightarrow \text{Pb}$	(R) Heating in presence of dry HCl followed by electrolysis
(D) $\text{MgCl}_2 \cdot 6\text{H}_2\text{O} \rightarrow \text{Mg}$	(S) Calcination followed by carbon reduction
(1) A-R, B-P, C-S, D-Q	(2) A-Q, B-P, C-S, D-R
(3) A-P, B-Q, C-S, D-R	(4) A-S, B-P, C-Q, D-R
- In the metallurgy of iron, during smelting process, CO is main reducing agent at the upper part of blast furnace, because
 (1) It is less concentrated in upper atmosphere
 (2) The CO_2 formed can be easily removed
 (3) In the lower atmosphere, there is no oxide to be reduced
 (4) The entropy change during CO/CO_2 is negative

4. Favourable reducing agent for ZnO/Zn is :-
 (1) C at high temperature (2) CO at high temperature
 (3) Cu at high temperature (4) Cu at low temperature
5. Which of the following is true regarding recovery of copper from its low grade (lean) ores.
 (1) Zn is advantageous economically
 (2) Fe is advantageous economically
 (3) Both Fe and Zn can be used and are equally advantageous
 (4) None of them can be used because Cu is less reactive
6. The slope of a line on Ellingham diagram for a process M/MO is :-
 (1) $-\frac{\Delta G}{R}$ (2) $-\Delta S$ (3) ΔS (4) $-\frac{\Delta S}{T}$
7. The true statement is at temperature 'T'
 (1) $M'(s) + \frac{1}{2}O_2(g) \rightarrow M'O(s)$ ΔS is positive
 (2) $M'(s) + MO(s) \rightarrow M'O(s) + M(s)$ ΔG is positive
 (3) $M'O(s) + MO(s) \rightarrow M'O(s) + M(s)$ ΔG is negative
 (4) $M'(s) + O_2(g) \rightarrow M'O(s)$ ΔS is negative
8. Auto reduction process is used in extraction of :
 (1) Cu (2) Hg (3) Pb (4) All of these
9. Which is not the correct process-mineral matching in metallurgical extraction.
 (A) Leaching : silver (B) Zone refining : lead.
 (C) Liquation : tin (D) Van Arkel : Zr
10. Consider the following metallurgical processes :-
 (i) Heating impure metal with CO and distilling the resulting volatile carbonyl (boiling point 43°C) and finally decomposing at 150°C to 200°C to get the pure metal.
 (ii) Heating the sulphide ore in air until a part is converted to oxide and then further heating in the absence of air to let the oxide react with unchanged sulphide.
 (iii) Electrolysing the molten electrolyte containing approximately equal amounts of the metal chloride and CaCl_2 to obtain the metal.
 The process used for obtaining sodium, nickel and copper are, respectively,
 (1) (i), (ii) and (iii) (2) (ii), (iii) and (i) (3) (iii), (i) and (ii) (4) (ii), (i) and (iii)



ANSWER KEY

BEGINNER'S BOX-1	Que.	1	2	3	4	5	6	7	8	9	10
	Ans.	2	3	3	1	4	4	4	4	2	1
BEGINNER'S BOX-2	Que.	1	2	3	4	5	6	7	8	9	10
	Ans.	3	3	3	2	3	2	2	3	4	3
BEGINNER'S BOX-3	Que.	1	2	3	4	5	6	7	8	9	10
	Ans.	1	2	4	1	2	2	4	4	2	3

SOME IMPORTANT ALLOY

- | | | | |
|----|---------------------|---|---|
| 1. | Bronze | - | Cu (75-90 %) + Sn (10-25 %) |
| 2. | Brass | - | Cu (60-80 %) + Zn (20-40%) |
| 3. | Gun metal | - | (Cu + Zn + Sn) (87:3:10) |
| 4. | German Silver | - | Cu + Zn + Ni (2:1:1) |
| 5. | Nichrome | - | (Ni + Cr + Fe) |
| 6. | Alloys of steel | | |
| | (a) Chromium steel | | Cr (2-4%) |
| | (b) Nickel Steel | | Ni (3-5%) |
| | (c) Stainless steel | | Cr (12-14%) & Ni (2-4%) Cr forms oxide layer & Protects Iron From Rusting |
| | (d) Invar (इनवार) | | Ni (36%) |

APPENDIX

LIST OF ORES AND THEIR NAMES

TYPES OF ORES	S.N.	FORMULA OF THE ORE	NAME
Oxide Ore	1.	ZnO (Philosopher's Wool)	Zincite
	2.	MnO ₂	Pyrolusite
	3.	SnO ₂	Cassiterite (Tin stone)
	4.	Cu ₂ O	Cuprite (Ruby Copper)
	5.	Fe ₂ O ₃	Haematite
	6.	Al ₂ O ₃ ·2H ₂ O	Bauxite
	7.	FeO·Cr ₂ O ₃	Chromite
	8.	Fe ₃ O ₄	Magnetite
	9.	Fe ₂ O ₃ ·3H ₂ O	Limonite
	10.	TiO ₂	Rutile
Sulphide Ore	1.	ZnS	Zinc Blende (Sphalerite)
	2.	HgS	Cinnabar
	3.	PbS	Galena
	4.	Ag ₂ S	Argentite or Silver glance
	5.	FeS ₂	Iron pyrites (Fool's gold)
	6.	CuFeS ₂ , CuS·FeS	Copper pyrites (Chalcopyrites)
	7.	Cu ₂ S·Ag ₂ S	Copper silver glance
	8.	Ag ₂ S·Sb ₂ S ₃	Pyrargirite (Ruby silver)
	9.	Cu ₂ S (Copper glance)	Chalcocite
Halide Ore	1.	NaCl	Rock Salt
	2.	AgCl	Horn Silver
	3.	CaF ₂	Flourspar
	4.	AlF ₃ ·3NaF	Cryolite
	5.	KCl·MgCl ₂ ·6H ₂ O	Carnelite
Carbonate Ore	1.	MgCO ₃	Magnesite
	2.	CaCO ₃	Lime stone
	3.	MgCO ₃ ·CaCO ₃	Dolomite
	4.	ZnCO ₃ (Smithsonite)	Calamine
	5.	PbCO ₃	Cerrusite
	6.	FeCO ₃	Siderite
	7.	CuCO ₃ ·Cu(OH) ₂	Malachite
	8.	2CuCO ₃ ·Cu(OH) ₂	Azurite
Sulphate Ore	1.	CaSO ₄ ·2H ₂ O	Gypsum
	2.	MgSO ₄ ·7H ₂ O	Epsomite Or Epsom salt
	3.	K ₂ SO ₄ ·Al ₂ (SO ₄) ₃ ·24H ₂ O	Alum
Nitrate Ore	1.	NaNO ₃	Chile- Salt Peter
	2.	KNO ₃	Salt peter or Indian salt peter
Phosphate Ore	1.	Ca ₃ (PO ₄) ₂	Rock Phosphate

EXERCISE-I (Conceptual Questions)

Build Up Your Understanding

1. Which of the following is not an ore of Iron:-
(1) Haematite (2) Limonite
(3) Cassiterite (4) Magnetite
2. Aluminium is obtained from Al_2O_3 by this method
(1) Thermal reduction.
(2) Hydro metallurgical method.
(3) Electrolytic reduction.
(4) Reduction by iron.
3. Zinc blende on roasting in air gives :-
(1) Zinc carbonate (2) SO_2 and ZnO
(3) ZnS and $ZnSO_4$ (4) CO_2 and ZnO
4. Litharge is a mineral of:-
(1) Magnesium (2) Lithium
(3) Lead (4) Zinc
5. The oxide cannot be reduced by coke
(1) Cu_2O , ZnO (2) Fe_2O_3 , ZnO
(3) CaO, K_2O (4) PbO, Fe_3O_4
6. Chemical formula of horn silver is:-
(1) Ag_2S (2) AgCl
(3) $AgNO_3$ (4) $Ag_2S \cdot Sb_2S_3$
7. An example of halide ores is:-
(1) Galena (2) Bauxite
(3) Cinnabar (4) Cryolite
8. Which is not a basic flux :-
(1) Silica (2) Lime stone
(3) Calcite (4) Quick lime
9. Iron pyrites ore is concentrated by:-
(1) Froth floatation (2) Electrolysis
(3) Roasting (4) Magnetic separation
10. Which of the following metal is extracted by electrolytic reduction process of its halide are :-
(1) Copper (2) Iron
(3) Sodium (4) Aluminium
11. Which of the following metal can not be extracted by smelting process:-
(1) Lead (2) Zinc
(3) Iron (4) Aluminium
12. The main reducing agent for the extraction of iron metal in a blast furnace is:-
(1) Coke (2) Carbon
(3) Carbon dioxide (4) Carbon monoxide
13. The flux used in extraction of Iron from haematite in the blast furnace is:-
(1) Silica (2) Lime stone
(3) Phosphorus chloride (4) Calcium phosphate
14. The reduction of Cr_2O_3 , by heating it with aluminium is known as:-
(1) Smelting
(2) Roasting
(3) Calcination
(4) Aluminothermite process
15. Which of the following is obtained by hydrometallurgy :-
(1) Copper (2) Gold
(3) Silver (4) All of these
16. Aluminium is purified by :-
(1) Roasting
(2) Sublimation
(3) Electrolytic refining
(4) Reduction with carbon
17. In Goldschmidt thermite process, reducing agent is:-
(1) Fe (2) Na
(3) Ca (4) Al
18. Heating pyrites in air to remove sulphur is known as:-
(1) Roasting (2) Calcination
(3) Smelting (4) Fluxing
19. Liquation process is used for refining:-
(1) Bismuth (2) Lead
(3) Tin (4) All
20. A mineral is called ore if
(1) Metal present in the mineral is costly
(2) A metal can be extracted from it
(3) A metal can be extracted profitably from it
(4) A metal can not be extracted from it
21. Autoredution process is used in the extraction of:-
(1) Cu & Pb (2) Zn & Hg
(3) Cu & Al (4) Fe & Pb
22. In thermite process, thermite mixture is:-
(1) Al powder + sulphide (2) Zn + oxide powder
(3) Na + Oxide (4) Al powder + oxide
23. The process of converting hydrated Alumina into anhydrous Alumina is called:-
(1) Roasting (2) Calcination
(3) Smelting (4) Dressing
24. The metallurgical process in which a metal is obtained in a fused state is called:-
(1) Smelting (2) Roasting
(3) Calcination (4) Froth floatation

- 25.** In the extraction of copper, metal is formed in the Bessemer converter due to reaction:-
 (1) $\text{Cu}_2\text{S} + 2\text{Cu}_2\text{O} \rightarrow 6\text{Cu} + \text{SO}_2$
 (2) $\text{Cu}_2\text{S} \rightarrow 2\text{Cu} + \text{S}$
 (3) $\text{Fe} + \text{Cu}_2\text{O} \rightarrow 2\text{Cu} + \text{FeO}$
 (4) $2\text{Cu}_2\text{O} \rightarrow 4\text{Cu} + \text{O}_2$
- 26.** In the electrolytic refining of copper, Ag and Au are found:-
 (1) On cathode (2) On anode
 (3) In the anodic mud (4) In the cathodic mud
- 27.** Consider :-
 (a) Copper blende = Cu_2O
 (b) Chromite = Magnetic separation.
 (c) Bauxite = $\text{Al}_2\text{O}_3 \cdot 2\text{H}_2\text{O}$
 (d) Liquation = Liquid metals e.g. Hg
 Which is/are not correctly matched :-
 (1) (a) only (2) (b) only
 (3) (d) only (4) (a) & (d) both
- 28.** Silver can be separated from lead by :-
 (1) Distillation (2) Amalgamation
 (3) Filtration (4) Cupellation
- 29.** In blast furnace this is acting as reducing agent at lower part :-
 (1) CO (2) H_2
 (3) C (4) None
- 30.** Which of the following metals can not be extracted by carbon reduction process :-
 (1) Pb (2) Al
 (3) Sn (4) Zn
- 31.** The maximum temperature obtained in the....region of the blast furnace used in extraction of iron:-
 (1) Reduction (2) Combustion
 (3) Fusion (4) Slag formation
- 32.** The concentration of chromite ($\text{FeO} \cdot \text{Cr}_2\text{O}_3$) is done by :-
 (1) Leaching process (2) Magnetic separation
 (3) Froth -flotation (4) Calcination
- 33.** Which of the following process involves smelting
 (1) $2\text{PbS} + 3\text{O}_2 \rightarrow 2\text{PbO} + 2\text{SO}_2\uparrow$
 (2) $\text{Al}_2\text{O}_3 \cdot 2\text{H}_2\text{O} \rightarrow \text{Al}_2\text{O}_3 + 2\text{H}_2\text{O}$
 (3) $\text{Fe}_2\text{O}_3 + \text{CO} \rightarrow 2\text{Fe} + 2\text{CO}_2$
 (4) $\text{Cr}_2\text{O}_3 + 2\text{Al} \rightarrow \text{Al}_2\text{O}_3 + 2\text{Cr} + \text{Heat}$
- 34.** Out of the following, which ores are calcinated during extraction :-
 (a) Copper pyrites (b) Malachite (c) Bauxite
 Correct answer is :-
 (1) a, b, c (2) b, c
 (3) Only a (4) All
- 35.** Which of the following match are incorrect :-
 (a) Goldschmidt aluminothermite process - Cr_2O_3
 (b) Mac Arthur cyanide process - Fe
 (c) Mond process - Ni
 (d) Van Arkel process - Au
 (1) a, c (2) c, d
 (3) b, d (4) a, b
- 36.** Electro metallurgical process (electrolysis of fused salt) is employed to extract :-
 (1) Lead (2) Silver
 (3) Sodium (4) Copper
- 37.** In the extraction of copper from pyrites, iron is removed as:-
 (1) FeSO_4 (2) FeSiO_3
 (3) Fe_3O_4 (4) Fe_2O_3
- 38.** Which one of the following metals can not be extracted by using Al as a reducing agent :-
 (1) Na from Na_2O (2) Cr from Cr_2O_3
 (3) Mn from MnO_2 (4) V from V_2O_5
- 39.** In the electrolytic refining for aluminium extraction the electrolyte used is:-
 (1) Fluorides of Al, Na and Ca
 (2) $\text{Al}(\text{OH})_3$ in NaOH solution
 (3) An aqueous solution of $\text{Al}_2(\text{SO}_4)_3$
 (4) Molten Al_2O_3
- 40.** Which one is mismatched :-
 (1) Poling - refining of copper
 (2) Cupellation - refining of silver
 (3) Smelting - An oxidation process
 (4) Roasting - An oxidation process
- 41.** Which metal can be purified by distillation :-
 (1) Cu (2) Ag
 (3) Fe (4) Hg
- 42.** Carbon cannot be used in the reduction of Al_2O_3 because :-
 (1) it is an expensive
 (2) the enthalpy of formation of CO_2 is more than that of Al_2O_3
 (3) pure carbon is not easily available
 (4) the enthalpy of formation of Al_2O_3 is too high
- 43.** Match list I with list II and select the correct answer using the codes given below the lists
- | | |
|---------------------|---|
| List I | List II |
| A. Van Arkel method | I. Purification of titanium |
| B. Solvay process | II. Manufacture of Na_2CO_3 |
| C. Cupellation | III. Purification of copper |
| D. Poling | IV. Refining of silver |
- Codes :**
- | | | | |
|---------|----|-----|-----|
| A | B | C | D |
| (1) I | II | IV | III |
| (2) II | I | III | IV |
| (3) IV | II | I | III |
| (4) III | I | II | IV |

44. Anode mud obtained after electrolytic refining of copper contains :-

- (1) Ag (2) Au
(3) Pt (4) All

45. Matte :-

- (1) $\text{Cu}_2\text{S} + \text{FeS}$
(2) $\text{Cu}_2\text{O} + \text{FeS}$
(3) $\text{Cu}_2\text{O} + \text{Cu}_2\text{S}$
(4) $\text{FeS} + \text{SiO}_2$

46. Which of the following reaction is not involved in thermite process :-

- (1) $3\text{Mn}_3\text{O}_4 + 8\text{Al} \longrightarrow 9\text{Mn} + 4\text{Al}_2\text{O}_3$
(2) $\text{Cr}_2\text{O}_3 + 2\text{Al} \longrightarrow \text{Al}_2\text{O}_3 + 2\text{Cr}$
(3) $2\text{Fe} + \text{Al}_2\text{O}_3 \longrightarrow 2\text{Al} + \text{Fe}_2\text{O}_3$
(4) $\text{B}_2\text{O}_3 + 2\text{Al} \longrightarrow 2\text{B} + \text{Al}_2\text{O}_3$

47. Alumino thermite process is used for the extraction of metals, whose oxides are :-



- (1) Strongly acidic
(2) Not easily reduced by carbon
(3) Not easily reduced by hydrogen
(4) Strongly basic

48. Match the following :-

I	II
(A) Calcination	a. $2\text{Cu}_2\text{S} + 3\text{O}_2 \rightarrow 2\text{Cu}_2\text{O} + 2\text{SO}_2$
(B) Roasting	b. $\text{Fe}_2\text{O}_3 \cdot n\text{H}_2\text{O} \rightarrow \text{Fe}_2\text{O}_3 + n\text{H}_2\text{O}$
(C) Flux	c. $\text{Cr}_2\text{O}_3 + 2\text{Al} \rightarrow \text{Al}_2\text{O}_3 + 2\text{Cr}$
(D) Thermite	d. $\text{SiO}_2 + \text{FeO} \rightarrow \text{FeSiO}_3$

A	B	C	D
(1) a	b	c	d
(2) b	a	d	c
(3) d	a	b	c
(4) c	a	b	d

49. Main source of lead is PbS . It is converted to Pb by :-



Self reduction process is :

- (1) A (2) B
(3) both (4) none

50. When haematite ore is burnt in air with coke along with lime at 200°C , the process not only produces steel but also produces an important compound (A), which is useful in making building materials. The compound (A) is

- (1) SiO_2 (2) CaSiO_3
(3) FeO (4) Fe_2O_3

51. Match List-I with List-II and select the correct answer using the codes given below the lists.

List-I (Metals)

List-II

(Process/methods involved in extraction process)

- (a) Au 1. Self reduction
(b) Al 2. Liquefaction
(c) Pb 3. Electrolysis
(d) Sn 4. Bayer's process


	(a)	(b)	(c)	(d)
(1)	3	1	2	4
(2)	3	4	1	2
(3)	1	2	4	3
(4)	3	2	4	1

52. Main function of the collectors in metallurgy is:

- (1) Stick to the ore and then take it to rise upto the top
(2) Convert the insoluble ore into soluble part
(3) Make the ore hydrophobic
(4) None

53. Reducing agent of haematite in blast-furnace is :-

- (1) Coke in furnace
(2) Coke in upper part and CO in lower part of furnace.
(3) CO in most parts of the furnace
(4) CO in the furnace.



- (1) PbO
(2) PbO_2
(3) PbO and PbSO_4
(4) PbO_2 and PbO

55. Which one of the following statements is **incorrect**?

- (1) Tin is extracted by carbon reduction (smelting)
(2) Aluminium is extracted by Hall's process which involves carbon reduction.
(3) Extraction of lead does not involve bessemerisation.
(4) Silver is extracted by cyanide process.

56. Extraction of zinc from zinc blende is achieved by:
- (1) electrolytic reduction
 - (2) roasting followed by reduction with carbon
 - (3) roasting followed by reduction with another metal
 - (4) roasting followed by self-reduction

57. Column - I

- (1) Metal which occur in the native state in nature is
- (2) The oxides of metal that can be commercially reduced by Aluminothermite reduction process is
- (3) van Arkel method is used for preparing ultrapure metal of
- (4) Auto reduction process is employed for the sulphide ore of

Column - II

- (P) Hg
 - (Q) Ti
 - (R) Cr
 - (S) Ag
- (1) A-S, B-R, C-Q, D-P
 - (2) A-R, B-S, C-Q, D-P
 - (3) A-P, B-S, C-Q, D-R
 - (4) A-Q, B-R, C-S, D-P

58. Match the following

- | | | |
|-----------------|---|---------------|
| 1. Zincite | P | Sulphide ore |
| 2. Malachite | Q | halide ore |
| 3. Horn silver | R | Oxide ore |
| 4. Iron pyrites | S | Carbonate ore |
- (1) 1 - R; 2 - P; 3 - Q; 4 - S
 - (2) 1 - R; 2 - S; 3 - Q; 4 - P
 - (3) 1 - S; 2 - R; 3 - P; 4 - Q
 - (4) 1 - Q; 2 - S; 3 - P; 4 - R

59. In magnetic separation method which one is true
- (1) either ore is being attracted by magnetic field
 - (2) either gangue is being attracted by magnetic field
 - (3) Both
 - (4) None

60. In froth floatation method depressants are used for-
- (1) to enhance non wettability of mineral particles
 - (2) to make suspension of ore with water
 - (3) to take forth upside
 - (4) to separate two sulphide ore

61. Which reaction shows formation of blistered copper.

- (1) $2\text{FeS} + 3\text{O}_2 \longrightarrow 2\text{FeO} + 2\text{SO}_2\uparrow$
- (2) $2\text{Cu}_2\text{S} + 3\text{O}_2 \longrightarrow 2\text{Cu}_2\text{O} + 2\text{SO}_2\uparrow$
- (3) $2\text{Cu}_2\text{O} + \text{Cu}_2\text{S} \longrightarrow 6\text{Cu} + \text{SO}_2\uparrow$
- (4) $\text{Cu}_2\text{O} + \text{C} \longrightarrow 2\text{Cu} + \text{CO}\uparrow$

62. Which reaction is involved in extraction of Ag by cyanide process

- (1) $\text{AgBr} + \text{Na}_2\text{S}_2\text{O}_3 \longrightarrow \text{Na}_3[\text{Ag}(\text{S}_2\text{O}_3)_2]$
- (2) $\text{AgCl} + \text{NH}_4\text{OH} \longrightarrow [\text{Ag}(\text{NH}_3)_2] \text{Cl}$
- (3) $\text{Ag}_2\text{S} + \text{NaCN} \longrightarrow \text{Na}[\text{Ag}(\text{CN})_2]$
- (4) None

EXERCISE-I (Conceptual Questions)

ANSWER KEY

Que.	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
Ans.	3	3	2	3	3	2	4	1	1	3	4	4	2	4	4
Que.	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30
Ans.	3	4	1	4	3	1	4	2	1	1	3	4	4	3	2
Que.	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45
Ans.	2	2	3	2	3	3	2	1	1	3	4	4	1	4	1
Que.	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60
Ans.	3	2	2	2	2	2	1	3	3	2	2	1	2	3	4
Que.	61	62													
Ans.	3	3													

EXERCISE-II (Previous Year Questions)

AIPMT/NEET & AIIMS (2006-2018)

AIPMT 2007

1. Sulphide ores of metals are usually concentrated by froth floatation process. Which one of the following sulphide ores offers an exception and is concentrated by chemical leaching?
- (1) Sphalerite (2) Argentite
(3) Galena (4) Copper pyrites

AIIMS 2010

2. According to percentage weight arrange the following in descending order in the earth crust
- (1) O₂, Ca, Mg, S (2) O₂, S, Mg, Ca
(3) S, Ca, Mg, O₂ (4) Ca, O₂, Mg, S

AIPMT-Pre 2011

3. Which of the following elements is present as the impurity to the maximum extent in the pig iron ?
- (1) Manganese (2) Carbon
(3) Silicon (4) Phosphorus
4. Which of the following pairs of metals is purified by Van Arkel method ?
- (1) Ga and In (2) Zr and Ti
(3) Ag and Au (4) Ni and Fe

AIPMT-Mains 2011

5. The following reactions take place in the blast furnace in the preparation of impure iron. Identify the reaction pertaining to the formation of the slag:-
- (1) $2C(s) + O_2(g) \rightarrow 2CO(g)$
(2) $Fe_2O_3(s) + 3CO(g) \rightarrow 2Fe(l) + 3CO_2(g)$
(3) $CaCO_3(s) \rightarrow CaO(s) + CO_2(g)$
(4) $CaO(s) + SiO_2(s) \rightarrow CaSiO_3(s)$

AIPMT-Pre 2012

6. Aluminium is extracted from alumina (Al₂O₃) by electrolysis of a molten mixture of:
- (1) Al₂O₃ + Na₃AlF₆ + CaF₂
(2) Al₂O₃ + KF + Na₃AlF₆
(3) Al₂O₃ + HF + NaAlF₄
(4) Al₂O₃ + CaF₂ + NaAlF₄

7. In the extraction of copper from its sulphide ore, the metal is finally obtained by the reduction of cuprous oxide with:
- (1) Iron sulphide (FeS)
(2) Carbon monoxide (CO)
(3) Copper (I) sulphide (Cu₂S)
(4) Sulphur dioxide (SO₂)
8. Identify the alloy containing a non-metal as a constituent in it.
- (1) Bell metal (2) Bronze
(3) Invar (4) Steel
9. Which one of the following is a mineral of iron?
- (1) Pyrolusite
(2) Magnetite
(3) Malachite
(4) Cassiterite

AIIMS 2014

10. Which of the following is separated as slag during extraction of Fe in blast furnace :-
- (1) SiO₂ (2) Al₂O₃
(3) CaO (4) MgO

Re-AIPMT 2015

11. In the extraction of copper from its sulphide ore, the metal is finally obtained by the reduction of cuprous oxide with :-
- (1) copper(I) sulphide
(2) sulphur dioxide
(3) iron(II) sulphide
(4) carbon monoxide

AIIMS 2015

12. In extraction of metal by bessemerisation, Cu₂S is converted into :
- (1) Cu₂O (2) CuO
(3) Cu (4) CuFeO₂

NEET-I 2016

13. Match items of **Column I** with the items of **Column II** and assign the correct code :

	Column-I		Column-II
(a)	Cyanide process	(i)	Ultrapure Ge
(b)	Froth floatation process	(ii)	Dressing of ZnS
(c)	Electrolytic reduction	(iii)	Extraction of Al
(d)	Zone refining	(iv)	Extraction of Au
		(v)	Purification of Ni

Code :

- | | | | |
|-----------|-------|-------|------|
| (a) | (b) | (c) | (d) |
| (1) (iv) | (ii) | (iii) | (i) |
| (2) (ii) | (iii) | (i) | (v) |
| (3) (i) | (ii) | (iii) | (iv) |
| (4) (iii) | (iv) | (v) | (i) |

NEET-II 2016

14. Zinc can be coated on iron to produce galvanized iron but the reverse is not possible. It is because:
- (1) zinc has lower negative electrode potential than iron
 - (2) zinc has higher negative electrode potential than iron
 - (3) zinc is lighter than iron
 - (4) zinc has lower melting point than iron

NEET(UG) 2017

15. Extraction of gold and silver involves leaching with CN^- ion. Silver is later recovered by :-
- (1) distillation
 - (2) zone refining
 - (3) displacement with Zn
 - (4) liquation

AIIMS 2017

16. Which of the following statement is correct about blast furnace.
- (1) CaCO_3 is used to produce O_2
 - (2) Fe_2O_3 convert into Fe_3O_4
 - (3) Wrought iron can directly be obtain from blast furnace
 - (4) Wrought iron is 100% pure
17. In the fusion of chromite ore with sodium carbonate in excess of air which of the following is not formed.
- (1) Fe_2O_3
 - (2) Na_2CrO_4
 - (3) CO_2
 - (4) $\text{Na}_2\text{Cr}_2\text{O}_7$

NEET(UG) 2018

18. Considering Ellingham diagram, which of the following metals can be used to reduce alumina ?
- (1) Fe
 - (2) Zn
 - (3) Mg
 - (4) Cu

AIIMS 2018

19. In the context of the Hall-Heroult process for the extraction of Al, which of the following statement is correct ?
- (1) the ratio of alumina & cryolite is nearly 1 : 9
 - (2) pure Al is obtained at anode
 - (3) melting point of alumina decreases upto 300 K
 - (4) only carbon monoxide gas is produced at graphite electrode
20. For smelting of Cu correct statements is :-
- (1) Cu is reduced
 - (2) FeS converted in FeO
 - (3) Fe is reduced
 - (4) Cu_2S converted in Cu_2O

EXERCISE-II (Previous Year Questions)

ANSWER KEY

Que.	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
Ans.	2	1	2	2	4	1	3	4	2	1	1	3	1	2	3
Que.	16	17	18	19	20										
Ans.	2	4	3	1	2										

EXERCISE-III (Analytical Questions)

- In the extraction of silver, Ag_2S is dissolved in :
(1) HCl (2) HNO_3
(3) KCN (4) H_2SO_4
- The method of zone refining of metals is based on the principle of :-
(1) Greater mobility of the pure metal than that of the impurity
(2) Higher melting point of the impurity than that of the pure metal
(3) Greater noble character of the solid metal than that of the impurity
(4) Greater solubility of the impurity in the molten state than in the solid
- Which one of the following ores is best concentrated by froth-flotation method :
(1) Galena (2) Cassiterite
(3) Magnetite (4) Malachite
- Which of the following sulphides when heated strongly in air gives the corresponding metal ?
(1) Cu_2S (2) CuS
(3) FeS (4) HgS
- Stainless steel does not rust because :
(1) Chromium and nickel combine with iron
(2) Chromium forms an oxide layer and protects iron from rusting
(3) Nickel present in it, does not rust
(4) Iron forms a hard chemical compound with chromium present in it
- In the electrolytic method of obtaining aluminium from purified bauxite, cryolite is added to the charge in order to -
(1) Minimise the heat loss due to radiation
(2) Protect aluminium produced from oxygen
(3) dissolve bauxite and render it conductor of electricity
(4) Increases the melting point of bauxite
- Purification of Ge like semiconductor is done by
(1) Cyanide process (2) Van arkel process
(3) Alumino thermite (4) Zone refining
- Which of the following contains both Cu & Fe :-
(1) Chalcocite (2) Chalcopyrites
(3) Malachite (4) Epsum

Check Your Understanding

- The metal that cannot be obtained by electrolysis of an aqueous solution of its salts is:
(1) Cu (2) Cr (3) Ag (4) Ca
- Which series of reactions correctly represents chemical relations related to iron and its compound?
(1) $\text{Fe} \xrightarrow{\text{Cl}_2, \text{heat}} \text{FeCl}_3 \xrightarrow{\text{heat, air}} \text{FeCl}_2 \xrightarrow{\text{Zn}} \text{Fe}$
(2) $\text{Fe} \xrightarrow{\text{O}_2, \text{heat}} \text{Fe}_3\text{O}_4 \xrightarrow{\text{CO, } 600^\circ\text{C}} \text{FeO} \xrightarrow{\text{CO, } 700^\circ\text{C}} \text{Fe}$
(3) $\text{Fe} \xrightarrow{\text{dil H}_2\text{SO}_4} \text{FeSO}_4 \xrightarrow{\text{H}_2\text{SO}_4, \text{O}_2} \text{Fe}_2(\text{SO}_4)_3 \xrightarrow{\text{Heat}} \text{Fe}$
(4) $\text{Fe} \xrightarrow{\text{O}_2, \text{heat}} \text{FeO} \xrightarrow{\text{dil H}_2\text{SO}_4} \text{FeSO}_4 \xrightarrow{\text{Heat}} \text{Fe}$
- In which of the following extration no reducing agent is required ?
(1) Iron from haematite
(2) Aluminium from Cinnabar
(3) Magnesium from carnallite
(4) Zinc from zinc blende
- Of the following reduction processes, the correct process(es) is/are :-
(1) $\text{B}_2\text{O}_3 + \text{Al} \xrightarrow{\Delta} \text{B}$
(2) $\text{Cr}_2\text{O}_3 + 2\text{Al} \xrightarrow{\Delta} \text{Cr}$
(3) $\text{TiCl}_4 + \text{Mg} \xrightarrow{\Delta} \text{Ti}$
(4) All the above
- Select the correct statement :-
(1) Dolomite contains both magnesium and calcium
(2) Extraction of lead from galena involves roasting in limited supply of air at moderate temperature.
(3) Extraction of zinc from zinc blende involves roasting followed by reduction with carbon.
(4) All the above
- Which of the following is/are correctly matched ?
(1) Copper - Bessemer converter
(2) Iron - Blast furnance
(3) Chromium - Aluminothermic process
(4) All the above

EXERCISE-III (Analytical Questions)

ANSWER KEY

Que.	1	2	3	4	5	6	7	8	9	10	11	12	13	14	
Ans.	3	4	1	4	2	3	4	2	4	2	3	4	4	4	

EXERCISE-IV (Assertion & Reason)

Target AIIMS

Directions for Assertion & Reason questions

These questions consist of two statements each, printed as Assertion and Reason. While answering these Questions you are required to choose any one of the following four responses.

- (A) If both Assertion & Reason are True & the Reason is a correct explanation of the Assertion.
 (B) If both Assertion & Reason are True but Reason is not a correct explanation of the Assertion.
 (C) If Assertion is True but the Reason is False.
 (D) If both Assertion & Reason are false.

- Assertion :** All the ores are mineral
Reason : Ores contains metals in combined state
 (1) A (2) B (3) C (4) D
- Assertion :** Ores are generally converted into oxides, prior to reduction
Reason : Metal oxides can be easily reduced
 (1) A (2) B (3) C (4) D
- Assertion :** In the extraction of Ag the complex $\text{Na}[\text{Ag}(\text{CN})_2]$ is reacted with Zn
Reason : Zn is transition metal.
 (1) A (2) B (3) C (4) D
- Assertion :** In froth floatation process sodium ethyl xanthate is used as floating agent
Reason : Sulphide ores are water soluble
 (1) A (2) B (3) C (4) D
- Assertion :** Cryolite is used in electrolytic extraction of Al from alumina.
Reason : It dissolves alumina, decreases its mpt.
 (1) A (2) B (3) C (4) D
- Assertion :** CuFeS_2 is concentrated by froath floatation method
Reason : CuFeS_2 is main ore of copper
 (1) A (2) B (3) C (4) D
- Assertion :** Wolframite impurities are separated from cassiterite by electromagnetic separation.
Reason : Cassiterite being magnetic is attached by the magnet.
 (1) A (2) B (3) C (4) D
- Assertion :** Lead, tin and bismuth are purified by liquation method.
Reason : Lead, tin and bismuth have low m.p. as compared to impurities.
 (1) A (2) B (3) C (4) D
- Assertion :** In the smelting of copper ore coke is added in the blast furnace.
Reason : Coke reduces, CuO into Cu.
 (1) A (2) B (3) C (4) D
- Assertion :** Extraction of iron metal from iron oxide ore is carried out by heating with coke.
Reason : The reaction $\text{Fe}_2\text{O}_3(\text{s}) \longrightarrow \text{Fe}(\text{s}) + 3/2\text{O}_2(\text{g})$ is a spontaneous process.
 (1) A (2) B (3) C (4) D
- Assertion :-** $\text{Cr}_2\text{O}_3 + 2\text{Al} \rightarrow \text{Al}_2\text{O}_3 + 2\text{Cr}$, this reaction is not possible at room temperature.
Reason :- ΔG value for this reaction is negative.
 (1) A (2) B (3) C (4) D
- Assertion :-** Zone refining is based on the fact that impurities are more soluble in molten state than in solid in the presence of oxygen.
Reason :- This method is used to prepare pure metal oxides.
 (1) A (2) B (3) C (4) D
- Assertion :-** According to ellingam diagram FeO can be easily reduced than Cu_2O by carbon.
Reason :- ΔG° of FeO is -300 kJ where as that of Cu_2O is -450 kJ .
 (1) A (2) B (3) C (4) D

EXERCISE-IV (Assertion & Reason)

ANSWER KEY

Que.	1	2	3	4	5	6	7	8	9	10	11	12	13	
Ans.	2	1	3	3	1	2	3	1	3	3	2	4	4	

This image shows a blank sheet of white paper with horizontal ruling lines. The lines are evenly spaced and run across the width of the page. There are no margins, text, or other markings on the paper.

[illegible]